



INNOVATIONS FOR LIVING™

PRODUCT INFORMATION


979

Chopped Strands for BMC

PRODUCT DESCRIPTION

979 is a high performance chopped strand reinforcement engineered for optimum performance in BMC compression, injection and transfer moulding applications. 979 sizing is specially formulated for maximum compatibility with polyester and vinylester resin systems.

979 chopped strand reinforcements can be used in a wide variety of applications including appliance components, automotive headlight reflectors and valve covers; electrical junction boxes and switch components; hand tool housing, sinks and countertops.



PRODUCT REFERENCE

Example : EC 14 6 mm 979
E : Glass type
C : Type of process: continuous
14 : Filament diameter (µm)
6 : nominal length of chop
979 : Owens Corning code for sizing system



FEATURES AND PRODUCT BENEFITS

- Easy mixing into the resin
- Because of their whiteness 979 chopped strands do not colour the compound
- No pollution, e.g. coloured particles
- Improved mechanical properties in both compression-moulded and injection-moulded parts.

TECHNICAL CHARACTERISTICS (nominal values)

Loss on Ignition (%)	Moisture content (%)
ISO 1887: 1995	ISO 3344: 1977
1.5	≤ 0.15

979

Chopped Strands for BMC

PRODUCT AVAILABILITY (standard ref.)

Reference	Filament diameter (µm)	Chopped length
979	14	3 6 12

PACKAGING

Examples of collective packaging:

Product		Bag net weight (kg)	Number of boxes per pallets	Pallet dimension L x W x H (cm)	Pallets*net weight (kg)
979	3 mm	20	30	120 x 90 x 115	600
	6 mm	20	30		600
	12 mm	15	36		540

* Add 46 kg to obtain gross weight.

LABELLING

- Each bag has one identification label showing the product reference and the nominal net weight in kg.
- Each pallet has two identification labels detailing the product reference, the net and gross weights in kg, the pallet identification code.

STORAGE

The chopped strands should be stored in its original packaging in a dry and cool place. Best conditions are at temperature from 10 to 35°C and humidity between 35 and 85 %. If you store the product at lower temperatures, please move the soon to be processed pallets to the production area 24 hours ahead of time. You can stock pallets one on one with a plywood plank in between the two.



INNOVATIONS FOR LIVING™

OWENS CORNING
COMPOSITE MATERIALS, LLC
ONE OWENS CORNING PARKWAY
TOLEDO, OHIO 43659
1.800.GET.PINK™

www.owenscorning.com
www.ocvreinforcements.com

Contact:
BMChoppedStrands.ocvamericas@owenscorning.com

EUROPEAN OWENS CORNING
FIBERGLAS, SPRL.

166, CHAUSSEE DE LA HULPE
B-1170 BRUSSELS
BELGIUM
+32.2.674.82.11

Contact:
BMChoppedStrands.ocvaemea@owenscorning.com

OWENS CORNING
COMPOSITE SOLUTIONS BUSINESS
ASIA PACIFIC REGIONAL HEADQUARTERS
UNIT 01,02,05,39/F, PUDONG KERRY PARKSIDE,
1155 FANG DIAN ROAD, PUDONG, SHANGHAI
201204, CHINA
+86.21.62489922

Contact:
BMChoppedStrands.ocvap@owenscorning.com

This information and data contained herein is offered solely as a guide in the selection of a reinforcement. The information contained in this publication is based on actual laboratory data and field test experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any responsibility or liability arising out of its use or performance. The user agrees to be responsible for thoroughly testing any application to determine its suitability before committing to production. It is important for the user to determine the properties of its own commercial compounds when using this or any other reinforcement. Because of numerous factors affecting results, we make no warranty of any kind, express or implied, including those of merchantability and fitness for a particular purpose. Statements in this publication shall not be construed as representations or warranties or as inducements to infringe any patent or violate any law safety code or insurance regulation.

Owens Corning reserves the right to modify this document without prior notice. ©2012 Owens Corning

BMChoppedStrands_979_ww_02-2012_Rev1